



Product:

Hardcoated Polyester Film LT

InteliCoat Technologies
Ash Road North
Wrexham Industrial Estate
Wrexham, LL13 9UF, UK

+44 (0)1978 660241 contact Gwen Simms
+44 (0) 1978 661452 fax

Web site: www.intelicoat.com

Reflex LT Hardcoated Polyester

Application

Membrane Touch Switch and Facia-panel manufacture

Features and Benefits

Excellent Print Receptive Coating
Chemical Resistant
UL Listed Base Film
Embossable

Abrasion Resistant
Optically Clear
UV & Solvent Based inks

Reflex is a range of high grade overlay films developed to meet the exacting requirements of Screen Printers, Membrane Touch Switch and Fascia-panel manufacturers and their end users.

Based on optical grade heat-stabilised polyester it has a typical residual shrinkage of less than 0.3%.

It is coated in 1000 Class Clean Rooms, on one side with a well proven print receptive layer for UV and solvent based inks and on the other side with an advanced UV cured resin.

InteliCoat has achieved the optimum performance in hardness, embossability, chemical resistance, extensive switch life and the ability to be die-cut.

These products are backed up by a programme of customer oriented development work to respond to customer needs.





Product:

Hardcoated Polyester Film LT

PROPERTIES	UNITS	TEST METHOD	TYPICAL VALUES		
<u>General</u>			LT 175	LT 125	
Total Thickness		Caliper	195	145	microns
PROPERTIES	UNITS	TEST METHOD	TYPICAL VALUES		
<u>Optical</u>					
Light Transmission		ASTM D1003	88		%
Gardner Haze		QCTM 137**	58		%
Gloss Level (60°)		ASTM D2457	19		%
Yellowness Index		ASTM E313-05	2.0	1.5	
<u>Mechanical</u>					
Switch Test		See note (d)	>3 Million		Flexes
Mar Resistance: Pencil		See notes (a)	4H		
	Taber Abrader	QCTM 149** See notes (b)	-4		%
	Rub Test	See notes (c)	> 1 Million		Rubs
Cross Hatch Adhesion		ASTM D3359	4B		
<u>Electrical</u>					
Volume Resistivity		ASTM D257*	10 ¹⁵		ohm/m
Surface Resistivity		ASTM D257*	10 ¹³		ohm/sq
Dielectric Strength		ASTM D149*	125		kV/mm
<u>Thermal</u>					
Usage Temperatures: Suggested Minimum			-40		°C
Suggested Maximum			150 (80 °C if embossed)		°C
<u>Dimensional Stability</u>					
MD		30minutes @ 120°C	- 0.3		%
TD		30minutes @ 120°C	+/- 0.1		%
Flammability		UL Flame Class*	HB		
<u>Chemical</u>					
Spot Test		ASTM 1308	See Technical Manual		
Immersion Test		MEK 24 hrs	Satisfactory		
Chemical Resistance		DIN42 115	See Technical Manual		

Notes

- (a) Pencil Test: Increasingly hard grades of pencil lead are scored across the surface of the coated PET. The point of the pencil is moved along the surface of the film with increasing force until the pencil breaks or until the surface of the coated film is scratched. The tests are continued until the pencil scratches the surface. The value given is the highest hardness value which does not scratch the coated film
- (b) Taber Test: A Taber abrader (CF10F Type 4 wheel; 250g load; 10 cycles) is used to abrade the test sample. Measurement of the haze value, before and after abrasion, are taken and the & change recorded. The average of three test samples is given
- (c) Rub Test: A test sample of the coated film is embossed to give a rim profile. The sample is then tested with repeated rubs with a standard rubber finger (45° Shore hardness) which travels along the surface of the film and over the rim. The 'finger' is weighted on a cantilever with a 500g weight. There should be no signs of wear and no evidence of coating delamination.
- (d) Switch Life: A standard rubber finger (45° Shore hardness) is used to flex an embossed dome switch continuously at a rate of 2 flexes/second. Pressure applied must be sufficient to force the apex of the dome to make contact with the support table. The switch should be examined at regular intervals to check for weight loss due to particles flaking off or cracking.